

Valox* FR1 Film

Product Datasheet

DESCRIPTION

Valox* FR-1 Film is a flame retardant thermoplastic polybutylene, terephthalite film offering UL94 VTM-0 performance down to 125 microns and good temperature performance. Valox FR-1 Film's outstanding dielectric strength and ease of fabrication (ie: thermoforming, embossing, clean-edge die-cutting, folding and bending) make it an excellent candidate for a wide range of electrical, electronic and medical applications.

Typical Property Values¹

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
Mechanical						
Tensile Strength						
@ Yield	ASTM D882	psi	7200	ISO 527	MPa	49.7
Ultimate	ASTM D882	psi	6000	ISO 527	MPa	41.1
Tensile Modulus	ASTM D882	psi	277000	ISO 527	MPa	1910
Tensile Elongation at Break	ASTM D882	%	57	ISO 527	%	57
Gardner Impact Strength at 0.03 in. (0.75 mm)	ASTM D3029	ft-lb	7	ISO 6603-1	J	10
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.46		kN/m	255
Propogation	ASTM D1922	g/mil	102.8		g/mil	102.8
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.007 inch (0.175 mm)	ASTM D2176-69	double folds	2000			
0.025 inch (0.625 mm)	ASTM D2176-69	double folds	83			
Thermal						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m ² K	0.17
Coefficient of Thermal Expansion	ASTM E831	(x 10 ⁻⁵ /°F)	3.1	ISO 11359	(x 10 ⁻⁵ /°C)	5.7
Specific Heat @ 40 °F (4 °C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.31
Glass Transition Temperature	ASTM D3417/D3418	°F	183	ISO 11357	°C	84
Vicat Softening Temperature, B	ASTM 1525-00 Modified	°F	346		°C	174
Heat Deflection Temp. by TMA at 1.8 MPa		°F	174	ISO 75 Modified	°C	79
Shrinkage at 302 °F (150 °C)	ASTM D1204	%	0.40%		%	0.40%
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

UL Flammability Rating / Performance Levels

Thickness	Rating	HWI	HAI
> 0.003" (0.075 mm) and < 0.005" (0.130 mm)	UL94VTM-2	-	-
> 0.005" (0.130 mm) and < 0.010" (0.250 mm)	UL94VTM-0	-	-
> 0.020" (0.500 mm) and < 0.025" (0.625 mm)	UL94VTM-0	4	0
0.025" (0.625 mm) and greater	UL94V-0	4	0
CTI: 2 HVTR: 4 D495: 6			
File Number	E61257		

Manufacturing Specifications

Nominal Gauge Ranges	Min./Max Limit of Nominal
0.003-0.010" (0.075-0.250 mm)	± 10%
0.015-0.030" (0.375-0.750 mm)	± 5%



1 These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local GE Advanced Materials, Specialty Film & Sheet representative or the GE Advanced Materials, Specialty Film & Sheet Quality Services Department. Reported values are based on 0.010" (0.250 mm) thickness unless otherwise noted.
* Valox is a trademark of General Electric Company.

GE Advanced Materials Specialty Film & Sheet

Property	ASTM Test Method	Units	Value	ISO Test Method	Units	Value
Physical						
Density	ASTM D792	slug/ft ³	2.6	ISO 1183	kg/m ³	1335
Water Absorption, 24 hrs.	ASTM D570	% change	0.48	ISO 62	% change	0.48
Surface Energy (1st surface / 2nd surface)	ASTM D5946-01	-	36/35			
Surface Tension (1st surface / 2nd surface)	Dyne Pens	Dyne	>44 / 34-36			
Pencil Hardness	ASTM D3363	-	2b-b			
Optical						
Light Transmission	ASTM D1003	%	15			
Yellowness Index	ASTM D1925	%	49			
Haze	ASTM D1003	%	103			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	5	ISO 2813	-	5
Electrical						
Dielectric Strength in oil, short time @ 72 °F (23 °C), 10 mils (0.25 mm)	ASTM D149-97a Method A	kV/mil	1.09	IEC 60243	kV/mm	43
Dielectric Constant						
@ 60 Hz	ASTM D150	-	3.3	IEC 60250	-	3.3
@ 1,000,000 Hz	ASTM D150	-	2.8	IEC 60250	-	2.8
Dissipation Factor						
@ 60 Hz	ASTM D150	-	0.0015	IEC 60250	-	0.0015
@ 1,000,000 Hz	ASTM D150	-	0.01	IEC 60250	-	0.01
Volume Resistivity	ASTM D257	Ω-cm	1E+17	IEC 60093	Ω-cm	1E+17
Surface Resistivity	ASTM D257	Ω/square	1E+16	IEC 60093	Ω/square	1E+16
Arc Resistance, Tungsten Electrodes	ASTM D495	s	21			

% Gloss by Gauge: (ASTMD 523-85)

	Gauge	Angle	Matte
FR1	0.003" (0.075 mm)	85°	Minimum
			Maximum
0.006-0.030" (0.150-0.750 mm)	85°	Minimum	0.1
		Maximum	17

Europe:

GE Advanced Materials
Specialty Film & Sheet
Plasticslaan 1
PO Box 112
NL - 4600 AC Bergen op Zoom
The Netherlands
Tel. (31) (164) 292742
Fax. (31) (164) 291986

Americas:

GE Advanced Materials
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 7110
Fax. (1) (413) 448 7506

Pacific:

GE Advanced Materials
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
Tel. (86) 21 6288 1088
Fax. (86) 21 6288 0818

For more information call:
(800) 451-3147

Visit us online at:
www.geadvancedmaterials.com

©2004 General Electric Company
All Rights Reserved

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP THE GE ADVANCED MATERIALS UNIT OF GENERAL ELECTRIC COMPANY, ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, GE ADVANCED MATERIALS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING GE ADVANCED MATERIALS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, GE ADVANCED MATERIALS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of GE Advanced Materials' products, materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating GE Advanced Materials' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of GE Advanced Materials' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by GE Advanced Materials. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of General Electric Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

* Trademark of General Electric Company.

