

LEXAN™ 60610 FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 60610 is a co-extruded film with improved scratch resistance and a high gloss surface finish. The film offers excellent clarity and optical quality in all thickness, high heat resistance, and superior dimension stability for graphics art applications. LEXAN 60610 film is available in gauges from 0.5 to 1.2 mm. Masking is of the stick type on both sides.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Ultimate	ASTM D882	psi	8860	ISO 527	MPa	61
Tensile Modulus	ASTM D882	psi	383000	ISO 527	MPa	2640
Tensile Elongation @ Break	ASTM D882	%	7.0	ISO 527	%	7.0
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb/in	37.4		J/mm	2
THERMAL						
Coefficient of Thermal Conductivity at 0.5mm	ASTM D5470	Btu/hr/ft ² /°F/in	1.42		W/m°K	0.21
Coefficient of Thermal Expansion at 0.4mm						
CTE -20~80°C, cross-flow	ASTM E831	(x10 ⁻⁵ /°F)	5.5	ISO 11359	(x10 ⁻⁵ /°C)	9.9
CTE -20~80°C, inflow	ASTM E831	(x10 ⁻⁵ /°F)	4.6	ISO 11359	(x10 ⁻⁵ /°C)	8.2
Glass Transition Temperature (PMMA/PC)	ASTM D3417 / D3418	°F	244/302	ISO 11357	°C	118/150
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.33	ISO 1183	kg/m ³	1190
Water Absorption, 24 hrs.	ASTM D570	% change	0.17	ISO 62	% change	0.17
Surface Roughness (RMS)	ASME B46-1	µm	0.01			
Surface Tension (PMMA/PC)	Dyne Pens	Dyne	36/38-40			
Pencil Hardness (PMMA/PC, 1Kg loading)	ASTM D3363	-	3H/2B			
OPTICAL						
Light Transmission	ASTM D1003	%	93			
Yellowness Index	ASTM D1925	%	<1.0			
Haze	ASTM D1003	%	<0.5			
Gloss over Flat Black min/max @ 60° (PMMA/PC)	ASTM D523-60	-	87.5/103	ISO 2813	-	87.5/103
ELECTRICAL						
Dielectric Constant @ 1.1 GHz	ASTM D150	-	2.78	IEC 60250	-	2.78
Dissipation Factor @ 1.1 GHz	ASTM D150	-	0.007	IEC 60250	-	0.007
Volume Resistivity	ASTM D257	Ω-cm	1.50E+16	IEC 60093	Ω-cm	1.50E+16
Surface Resistivity (PMMA/PC)	ASTM D257	Ω/square	2.1E+15/3.8E+15	IEC 60093	Ω/square	2.1E+15/3.8E+15

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported values are based on 0.500 mm (0.020") thickness film unless otherwise noted.

™ Trademark of SABIC.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.500 - 1.200 mm	± 3%

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
1 Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783
T 1 413 448 6655
F (888) 443 2033
E Spinside.sales@sabic-ip.com

Europe

Specialty Film & Sheet
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs

