

PRODUCT SPECIFICATION

SCREEN GRADE BANNER FILM

TEST	ASTM STANDARD	UNIT OF MEASURE	TYPICAL VALUE
Thickness		Inches	0.010
Elmendorf Tear	D1922	MD--g	1400-1600
		TD--g	2800-3000
Tensile Strength @ Break	D882	MD--psi	3400-3600
		TD--psi	3600-3800
Elongation @ Break	D882	MD--%	900-1000
		TD--%	1000-1100
Dart Impact	D1709-A	g	1100-1200
COF	D1894	Static	CUSTOM
Corona Treatment		Dynes	CUSTOM

NOTE: Values are typical and are not to be construed as an absolute specification.
This specification is supplied upon request for use as a general guideline.

Crayex screen grade banner film can be custom manufactured in a wide variety of sizes and thicknesses. We offer superior layflat, static control, treat options suitable for solvent or UV inks and film that is flexible for downstream sewing/heat seal/grommets. Our screen grade film is specifically designed for better "slide" of film over vacuum tables and is available in large O.D. roll configurations with short lead times. Contact your Crayex sales representative and they will be glad to provide more information and pricing upon request.