

# Technical Data Sheet



**Product name:** Pentaprint® Rigid Vinyl PR-M280/36

**Description:** Rigid vinyl film with high-impact strength for print applications  
**Color:** Clear  
**Surface:** Gloss/gloss

Properties	Standard	U.S.		SI	
		Unit	Value	Unit	Value
Gauge Range Available Rolls Sheets	Micrometer	mil	4-27 7-27	µm	102-686 178-686
Gauge Tolerance	D-374	%	±5	%	±5
Specific Gravity	D-1505	—	1.34	—	1.34
Material Yield (Nominal) 6 mil 10 mil 20 mil	D-1505	in <sup>2</sup> /lb	3,443 2,066 1,033	m <sup>2</sup> /kg	4.90 2.94 1.47
Tensile Strength (Yield)	D-882	lb/in <sup>2</sup>	6,600	N/mm <sup>2</sup>	46
Tensile Impact Strength	D-1822 MOD	ft*lb/in <sup>2</sup>	275	J/mm <sup>2</sup>	0.58
Tensile Elongation (Break)	D-882	%	180	%	180
Gloss (20°)	D-523	%	125	%	125
Cold Break Temperature	D-1790	°F	-4	°C	-20
Heat Deflection Temperature (264 psi)	D-648	°F	162	°C	72

**Regulatory:**

- Klöckner Pentaplast certifies that its rigid film and sheet products comply with the most recent package requirements for heavy metals of the Toxic Packaging Clearing House (TPCH, formerly CONEG) legislation and the latest March 9, 2005, requirements of the European Packaging Directive EU 94/62, as well as European Union Directive 2002/95/EC (RoHS – Reduction of Hazardous Substances).
- Klöckner Pentaplast rigid films and sheet products do not contain any Ozone depleting substances, including those listed in the 1990 Clean Air Act Amendments.
- No DEHP (Di-ethylhexyl phthalate) or DEHA (Di-ethylhexyl adipate) or any other phthalate or adipate additives are used in the manufacture of Klöckner Pentaplast rigid film and sheet products.
- No BPA (bisphenol A), alkyl phenols (octyl and nonyl), alkyl phenol ethoxylates (octyl and nonyl), or butyl benzyl phthalates are used in the manufacture of this kp film.

The statements contained herein are for informational purposes only and are true and accurate to the best of our scientific and technical knowledge. This information does not constitute a guarantee or warranty, express or implied, nor does it establish a legally valid contractual relationship. It is the customer's responsibility to determine the suitability of this product for the customer's intended use, and Klöckner Pentaplast does not assume any liability for the customer's use of this product or the information contained herein.  
Revision: 1\_9.25.09

# Technical Data Sheet



- 
- Storage conditions:**
- Ideal storage conditions between 10-30°C (50-86°F)
  - Ideal RH 40-70%
  - Should not be stored in direct sunlight
  - Film should be conditioned a minimum of 24 hours at ambient room temperature

The statements contained herein are for informational purposes only and are true and accurate to the best of our scientific and technical knowledge. This information does not constitute a guarantee or warranty, express or implied, nor does it establish a legally valid contractual relationship. It is the customer's responsibility to determine the suitability of this product for the customer's intended use, and Klöckner Pentaplast does not assume any liability for the customer's use of this product or the information contained herein.  
Revision: 1\_9.25.09